

SPECIFICATION		PAGE	1/3
PART NUMBER :	TDF203026	REV.	A

SPECIFICATION

PART NO: TDF203026

【Approval Stamp Column 】

Customer :



STODA Technologies(Shantou)LTD

Tel : 0754-89918282

Website: www.stodatech.com

Email: sales@stodatech.com

Address: Huanshi east road, Chen nan street , Chaoyang , Shan tou, Guang dong P.R.C

SPECIFICATION		PAGE	2/3
PART NUMBER :	TDF203026	REV.	A

1: PHYSICAL DIMENSION

BEFORE COATING


OUTSIDE DIAMETER	(OD)	:	20.32	mm	MAX
INSIDE DIAMETER	(ID)	:	12.7	mm	MIN
HEIGHT	(HT)	:	6.35	mm	MAX

AFTER COATING :

OUTSIDE DIAMETER	(OD)	:	21.08	mm	MAX
INSIDE DIAMETER	(ID)	:	12.07	mm	MIN
HEIGHT	(HT)	:	7.11	mm	MAX


2: CORE MAGNETIC PARAMETERS

EFFECTIVE MAGNETIC PATH LENGTH	(L_e)	:	5.09	cm
EFFECTIVE CROSS SEPCION AREA	(A_e)	:	0.226	cm ²
EFFECTIVE VOLUME	(V_e)	:	1.15	cm ³



3: DC BIASED INDUCTANCE


H_{DC}	:	200	Oe
PERCENT INITIAL PERM(NOM)	:	85.18%	
PERCENT INITIAL PERM(MIN.)	:	81.40%	



SPECIFICATION		PAGE	3/3
PART NUMBER :	TDF203026	REV.	A

4: CORE LOSS

B_{pk} : 500 G
 FREQUENCY : 100 kHz
 CORE LOSS (NOMINAL) : 495 mW/cm³
 CORE LOSS (MAXIMUM) : 570 mW/cm³



5: INDUCTANCE

μ_i (REFERENCE) : 26
 AL VALUE (NOMINAL) : 14 nH/N²
 FREQUENCY : 10kHz
 VOLTAGE ON TH2829A : 0.29V
 AL TOLERANCE : $\pm 8\%$
 TEST INSTRUMENT : TH2829A

6: COATING/PACKAGE

COATING TYPE : Blue Epoxy
 VOLTAGE BREAKDOWN (MIN.) : 1000 Vrms
 LIMIT : 0.1 mA, 5 s
 PACKAGE QUANTITY : 1500 Pcs/Box

7: MATERIAL DESCRIPTION

93.5%Fe, 6.5%Si

REVISION HISTORY			PREPARED	CHECKED	APPROVED
REV.	DESCRIPTION	DATE			
A	FIRST ISSUE	2022/6/8			